

kuraray

AUTOMOTIVE

PVB FILM FOR LAMINATED SAFETY GLASS

PRODUCT INFORMATION

TROSIFOL[®]



PROPERTIES:

high edge stability for excellent long life stability

moisture insensitive adhesion properties

high pre-press transparency and excellent optics of final laminate due to improved flow behaviour

easy edge trim after autoclaving

low occurrence of odour after shaping of film sheets

very low level of electrostatic charge

TROSIFOL® – YOUR PARTNER FOR AUTOMOTIVE GLAZING

TROSIFOL® offers a wide range of products and services for the use in automotive glazing applications that all comply to ISO/TS 16949, DIN EN ISO 9001:2000, DIN EN ISO 14001:2004 and OHSAS 18001:1999.

Windshields and side lights laminated with TROSIFOL® have excellent properties in respect of safety, security, long term stability, noise reduction and UV protection.

TROSIFOL® VG shows outstanding edge stability, good processing properties and excellent moisture resistance.

An innovative PVB film for automotive glazing: TROSIFOL® VG has been developed for all prevalent manufacturing processes and fulfils the requirements of all relevant quality standards, including ECE R 43 and ANSI Z26.1., and it is available in all standard colours and shade band combinations, either refrigerated or PE interleaved.



TROSIFOL® VG

- Shade band film is available in widths up to 2050 mm, with a max. shade band width of 250 mm
- TROSIFOL® VG clear is available in widths from 300 mm to 3210 mm
- TROSIFOL® VG is designed and optimised for all major manufacturing processes

Thickness [mm]	Colour	Light transmittance* [%]	Colour Code	Length of refrigerated roll [m]	Length of roll PE interleaved [m]
0.76	Clear	88	–	250/500	250
0.76	Light green	80	9.20.80	250	250
0.76	Light bronze	77	3.75.77	250	250
0.76	Light blue green	75	8.45.75	250	250
0.76	Colour band Green on clear	88	8.80.25.35	250	250
0.76	Colour band Blue on clear	88	7.80.05.19	250	250
0.76	Colour band Grey on clear	88	6.15.34.60	250	250
0.76	Colour band Dark grey on clear	88	6.15.18.30	250	250
0.76	Colour band Blue on light blue green	75	7.80.05.19 on 8.45.75	250	250
0.76	Colour band Green on light blue green	75	8.80.25.35 on 8.45.75	250	250

* LSG with 2 x 2 mm clear glass

TROSIFOL® PG 4015*

The PVB film was especially designed for the manufacture of laminated safety glass with coated polyester films (e.g. Southwall products). The film has an asymmetric surface structure in order to ensure excellent optical properties of the final product. It is available in clear or with colour band (on request), only in 0.38 mm film thickness.

* TROSIFOL® PG 4015 has successfully passed reliability tests with Southwall's XIR75 G2 Automotive Film. Test results are available on request.

TROSIFOL® PG

Thickness [mm]	Colour	Light transmittance* [%]	Colour Code	Shade band** [mm]	Length of refrigerated roll [m]	Length of roll PE interleaved [m]
0.38	Clear	88	–	–	300/470	300
0.38	Colour band (various) on clear**	88	Various	max. 260	300/470	300

* LSG with 2 x 2 mm clear glass

** available on request



TROSIFOL® – TECHNICAL DATA

TROSIFOL® VG

Product	Thickness [mm]	Water content [%]	Surface Roughness R _z * [μm]
TROSIFOL® VG-FR	0.76	0.45	40

Further automotive products on request.

TROSIFOL® PG

Product	Thickness [mm]	Water content [%]	Surface Roughness R _z * [μm]
TROSIFOL® PG	0.38	0.45	40 (A Side) 15 (B Side)

All details are typical averages.

* Values measured in accordance with EN ISO 4287



TROSIFOL® – LOGISTICS AND PACKAGING

TROSIFOL® products are heat sealed in bags impervious to water and water vapour.

DRUM PACKAGING – VERTICAL

Max. Width [mm]	Dimension [mm]	
	Diameter	Height
740	570	800
850	570	900
1000	570	1060
1150	570	1200
1320	570	1380
1420	570	1500



WOODEN PALLETS – VERTICAL (4 rolls per pallet)

Max. Width [mm]	Dimension [mm]		
	Length	Width	Height
700	1100	1100	750
800	1100	1100	850
950	1100	1100	1000
1050	1100	1100	1100
1230	1100	1100	1260



RETURNABLE PACKAGING

Max. Width [mm]	Length	Width	Height
1260	1420	780	985



CONTACT

For further information about TROSIFOL® products and services please contact:

Kuraray Europe GmbH

Division TROSIFOL®
Mülheimer Straße 26
53840 Troisdorf
Germany
Phone: ++49 (0) 22 41/25 55 – 220
Fax: ++49 (0) 22 41/25 55 – 299
E-Mail: trosifol@kuraray.eu

Kuraray India Private Ltd.

Division TROSIFOL®
207 B, Rectangle I
D-4, District Centre, Saket
New Delhi 11 00 17
India
Phone: ++91 11 4610 2900
Fax: ++91 11 4610 2911
E-Mail: trosifol.india@kuraray.eu

000 TROSIFOL®

Kolzowa, 24
606440 Bor
Nishny Novgorod Region
Russia
Phone: ++7 83159 6-77-28
Fax: ++7 83159 6-77-87
E-Mail: info@kuraray.ru

Kuraray Co., LTD

Ote Center Bldg.
1-1-3, Otemachi
Chiyoda-Ku
Tokyo, 100-8115
Phone: ++81 3 6701 1453
Fax: ++81 3 6701 1460
E-Mail: trosifol.japan@kuraray.eu

Kuraray Shanghai Co., Ltd.

Unit 2207, 2 Grand Gateway
3 Hongqiao Road
Xu Hui District
Shanghai 200030
China
Phone: ++86 021 61198111
Fax: ++86 021 61198585
E-Mail: trosifol.china@kuraray.eu

Kuraray America, Inc.

Division TROSIFOL®
2625 Bay Area Blvd.
Suite 300
Houston, Texas 77058-1551
Phone: ++1 800 423-9762
Fax: ++1 713 495-7322
E-Mail: TrosifolOrders@KurarayAmerica.com