

Kuraray Advanced Interlayer Solutions
Technical information

Bulletin

Blast performance of laminated glass



Photo: © Grand Warszawski - Serhii Yushkov / shutterstock.com

Kuraray Advanced Interlayer Solutions

Blast performance of laminated glass

In blast-resistant glazing materials and systems, laminated glass can be used to reduce the hazards associated with an explosion. Laminates made with Trosifol® PVB or SentryGlas® ionoplast interlayers are typically used in window, door, curtain wall, and storefront systems designed to provide a higher level of performance than standard systems. Shock tube and arena test results support the use of both PVB and ionoplast interlayers in blast-resistant glazing. This bulletin summarizes blast resistance test results for glazing systems made with Trosifol® PVB and SentryGlas® ionoplast interlayers.

SHOCK TUBE TESTING

Laminated glass panels made with Trosifol® PVB and SentryGlas® ionoplast interlayers were tested in a shock tube at Intertek's Laboratory in York, Pennsylvania. A peak pressure of 41 kPa (6 psi) and impulse of 282 kPa-msec (41 psi-msec) were chosen to represent performance levels found in the Unified Facilities Design Criteria (UFC) of the U.S. Department of Defense. The test specimens were 126 cm (49.72 inches) x 172 cm (67.75 inches), wet-glazed in a wooden frame.

Blast testing was conducted according to ASTM F1642 Standard Test Method for Glazing and Glazing Systems Subject to Airblast Loadings. This standard enables the user to determine a hazard rating for the glazing or system utilizing either a shock tube or arena test. ASTM Hazard Ratings are expressed differently than those of the U.S. General Services Administration (GSA). GSA Condition 3a equates to the Very Low Hazard level defined in ASTM F1642 where the glass cracks, and fragments land on the floor no further than 1 meter. GSA Condition 2 equates to ASTM F1642 No Hazard, where glass cracks but is retained in the frame. The results of the test program are presented in Table 1.

In addition, WINdow Glazing Analysis Response and Design (WINGARD) software was used to compare the actual shock tube results to those predicted by the software. The study confirmed a high level of correlation between the two. All three versions of the WINGARD software (WINGARD LE, PE, and MP) contain PVB and SentryGlas® ionoplast interlayer properties data.



➤ A shock tube focuses a blast-level pressure wave against a mounted glass sample.

Summary of results from Intertek shock tube testing

Glass	Interlayer thickness [mm]	Interlayer thickness [mil]	Interlayer Type	Hazard rating	GSA performance condition
3 mm – 3 mm 1/8" – 1/8"	0.76	30	Trosifol® PVB	very low hazard	3a
3 mm – 3 mm 1/8" – 1/8"	1.52	60	Trosifol® PVB	none	2
3 mm – 3 mm 1/8" – 1/8"	0.89	35	SentryGlas® ionoplast	none	2
6 mm – 6 mm 1/4" – 1/4"	0.76	30	Trosifol® PVB	none	2
6 mm – 6 mm 1/4" – 1/4"	1.52	60	Trosifol® PVB	none	2
6 mm – 6 mm 1/4" – 1/4"	0.89	35	SentryGlas® ionoplast	none	2

TAB 1 • Blast level: 41 kPa (6 psi) 282 kPa-msec (41 psi-msec)

ARENA TESTING

The overall performance of a selection of glazing systems was evaluated in arena tests conducted by HTL Laboratories in Lubbock, TX, according to ASTM F1642 Standard Test Method for Glazing and Glazing Systems Subject to Airblast Loadings. Results of the arena test program are shown in Table 2. Note that these systems also are designed to perform to various hurricane test protocols required for construction in certain regions of the United States.



• A laminated glass panel is inspected after shock tube blast testing (above), to assess glass fragmentation.



• In an arena test, fully installed glazing systems are exposed to an actual explosive blast, under controlled conditions at a high-security open-air test site.

Summary of results from arena testing of several commercial glazing systems incorporating various constructions of laminated glass using a SentryGlas® ionoplast interlayer

Manufacturer	System tested	Glass construction	SentryGlas® thickness		UFC 4-010-01 Level of protection	ASTM Hazard rating	GSA performance condition
			[mm]	[mil]			
AlumiGlass, Inc.	6400 Curtain wall	IGU	2.28	90	Medium	No Hazard	2
Coral Industries	FL550 Storefront Series 381 Entrance	IGU	1.52	60	Medium	Minimal	2
		Monolithic Laminate	1.52	60	Medium	Minimal	2
Crawford Tracey Corp.	ProTech 7SG Storefront	IGU	0.89	35	Medium	Minimal	2 & 3b
		IGU	2.28	90	Medium	Minimal	3b
	ProTech 45S G Storefront	IGU	0.89	35	Medium	Minimal	2
		IGU	2.28	90	Medium	Minimal	2
EFCO Corp.	5600 Series Curtain wall	IGU	2.28	90	Medium	Minimal	2
	D500 Entrance	IGU	0.89	35	Medium	Minimal	2
	Concealed Vent				Medium	Minimal	2
ES Windows	ES-7525 Curtain Wall	IGU	2.28	90	Medium	Minimal	2
	ES-7530 Unitized Curtain Wall	IGU	2.28	90	Medium	Minimal	2
	ES-9000 Entrance	IGU	2.28	90	Medium	Minimal	2
PGT Industries	PW-3020	Monolithic Laminate	2.28	90	High	No Break	1
West Tampa Glass	WTG-500 Curtain Wall	Monolithic Laminate	0.89	35	Medium	Minimal	2
		Monolithic Laminate	2.28	90	Medium	Minimal	2
		IGU	0.89	35	Medium	Minimal	2
		IGU	2.28	90	Medium	Minimal	2
	WTG-700 Curtain Wall	Monolithic Laminate	0.89	35	Low	Low	3b
		Monolithic Laminate	0.89	35	Medium	Minimal	2
		Monolithic Laminate	4.56	180	Medium	No Hazard	2
		IGU	0.89	35	Medium	No Hazard	2
		IGU	2.28	90	Medium	No Hazard	2
		IGU	2.28	90	Medium	No Hazard	2
		IGU	4.56	180	Medium	Minimal	2
		IGU	4.56	180	Medium	No Hazard	2
	WTG-900 Curtain Wall	Monolithic Laminate	0.89	35	High	No Break	1
		Monolithic Laminate	2.28	90	High	No Break	1
IGU		0.89	35	High	No Break	1	
IGU		2.28	90	High	No Break	1	
YKK	Results Upcoming						
Tubelite	Forcefront Blast Curtain Wall	IGU	1.52	60	Low	Very Low	3A
			0.89	35	Low	Very Low	3A
			1.52	60	Medium	Minimal	2
	Forcefront Blast Entrance	IGU	0.89	35	Medium	Minimal	2

TAB 2 • Blast level: 41 kPa (6 psi) 282 kPa-msec (41 psi-msec)

Contact



FOR FURTHER INFORMATION

on products from Kuraray, please visit www.kuraray.com.

You can find further information on our Trosifol® and SentryGlas® products at www.trosifol.com.

Kuraray America, Inc.

Advanced Interlayer Solutions Division
Wells Fargo Tower
2200 Concord Pike, Ste. 1101
Wilmington, DE 19803, USA
P +1 800 635 3182

trosifol@kuraray.com

Kuraray Europe GmbH

Advanced Interlayer Solutions Division
Kronenstr. 55
53840 Troisdorf
Germany
P +49 2241 2555 226

Kuraray Co., Ltd

Advanced Interlayer Solutions Division
Tokiwabashi Tower
2-6-4 Otemachi, Chiyoda-ku
Tokyo 100-0004, Japan
P +813 6701 1508

8/2023

Copyright © 2023 Kuraray. All rights reserved.

Trosifol, Butacite, SentryGlas, SG, SentryGlas Xtra, SGX, SentryGlas Acoustic, SGA and Spallshield are trademarks or registered trademarks of Kuraray Co., Ltd. or its affiliates. Trademarks may not be applied for or registered in all countries. The information, recommendations and details given in this document have been compiled with care and to our best knowledge and belief. They do not entail an assurance of properties above and beyond the product specification. Final determination of suitability of any material or process and whether there is any infringement of patents is the sole responsibility of the user.



WORLD OF INTERLAYERS

**What is the next project
you are dreaming of?**